

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

GMH3-OVERLAM 19OCT12

Non Printable Overlam Film

This specification is intended to outline the physical and chemical properties of PANDUIT's pressure sensitive polyester material and include the following part numbers:

Part Number Prefixes			

Printable Material Suffixes			
*YK			
YK-			

PRODUCT SPECIFICATIONS:

Description: Material is RoHS compliant (European Union directive 2002/95/EC).

Material is a 2 mil polyester film with a pressure sensitive adhesive.

It is issued as a protective overlaminate.

Adhesive: Acrylic based, pressure sensitive permanent adhesive.

Standard Colors: Clear

Thickness: 3.0 +/- 0.3 mils (substrate and adhesive)

-51°F to 275°F (-46°C to 135°C) Service Temperature Range:

Minimum Application Temperature: 35°F (2°C)

Storage Conditions: Store at 70°F (21°C) and 50% Relative Humidity.

PROPERTIES: PERFORMANCE:

Peel Adhesion to Stainless Steel: 40 oz/in. width minimum (PSTC-101, 15 min. dwell) 24 hours minimum (PSTC-107, Procedure A) Shear Adhesion: UV Resistance: *3000 hours, no change observed (ASTM G154)

After 8 hours at 275°F (135°C) there was no deterioration of the substrate Elevated Temperature Exposure:

Reference:

PSTC: Pressure Sensitive Tape Council (U.S.A.)

ASTM: American Society for Testing and Materials (U.S.A.)

Page 1 of 2 © 2007 PANDUIT Corp

TDS: GMY-OVERLAM

^{*3000} hours equates to 5 years of assimilated UV exposure.



Technical Data Sheet

18900 Panduit Drive Tinley Park, IL 60487

Customer Service: 800-777-3300

TDS: Effective Date: Revision:

GMH3-OVERLAM 19OCT12

LIMITED WARRANTY

All PANDUIT Identification Solution Products (except for Software programs) are warranted to be free from defects in material and workmanship at the time of sale but our obligation under this warranty is limited to replacement of the product proved to be defective within 6 months from the date of sale, or in the case of printers, within 90 days from the date of sale. This warranty is void if the products or printers are modified, altered or misused in any way. Use of PANDUIT printers with any product other than the specified PANDUIT products for which the printer was designed constitutes misuse. Before using, the user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be altered except by an agreement signed by officers or seller and manufacturer.

NEITHER PANDUIT OR SELLER SHALL BE LIABLE FOR ANY OTHER INJURY, LOSS OR DAMAGE, WHETHER DIRECT OR CONSEQUENTIAL, ARISING OUT OF THE USE OF, OR THE INABILITY TO USE THE PRODUCT OR THE PRINTER.

THIS WARRANTY IS MADE IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS OF PARTICULAR USE ARE SPECIFICALLY EXCLUDED.

The information contained in this literature is based on our experience to date and is believed to be reliable. It is intended as a guide or use by persons having technical skill at their own discretion and risk. We do not guarantee favorable results or assume any liability in connection with its use. Dimensions contained herein are for reference purposes only. This publication is not to be taken as a license to operate under, or a recommendation to infringe any existing patents. This supersedes and voids all previous literature, etc.

© 2007 PANDUIT Corp Page 2 of 2

TDS: GMY-OVERLAM