

Cable Accessories

	Test Method	Nylon 6.6	Weather Resistant Nylon 6.6	Impact Modified Weather Resistant Nylon 6.6	Heat Stabilized Nylon 6.6	Heat Stabilized Nylon 6.6	Heat Stabilized Weather Resistant Nylon 6.6	Impact Modified Heat Stabilized Weather Resistant Nylon 6.6	Flame Retardant Nylon 6.6
Color	—	Natural, White, Black, Gray	Black	Black	Black	Natural	Black	Black	Black
Part Number Suffix (Material) Designation	—	None 20, 14	0	0	30	39	300	350	60
Mechanical Properties									
Tensile at Yield 73°F (psi)	ISO 527	12,000	12,000	7,500	12,000	12,000	12,000	8,700	11,000
Water Absorption (24 Hours)	ASTM D570	1.2%	1.2%	1.2%	1.2%	1.2%	1.2%	1.2%	1.1%
Radiation Resistance Rads	—	1 X 10	1 X 10	1 X 10	1 X 10	1 X 10	1 X 10	1 X 10	1 X 10
Weathering Life Expectancy (Years)/UV Resistance	—	1-2	7-9	7-9	4-5	1-2	7-9	7-9	1-2
Impact Resistance	—	○	○	⊖	○	○	○	⊖	⊖
Chemical Resistance									
Salts	—	⊖	⊖	⊖	⊖	⊖	⊖	⊖	⊖
Hydrocarbons (Gas, Oil, Lubricants)	—	●	●	●	●	●	●	●	●
Chlorinated Hydrocarbons	—	⊖	⊖	⊖	⊖	⊖	⊖	⊖	⊖
Acids	—	●	●	●	●	●	●	●	●
Bases	—	⊖	⊖	⊖	⊖	⊖	⊖	⊖	⊖
Acid Rain	—	⊖	⊖	⊖	⊖	⊖	⊖	⊖	⊖
Thermal Properties									
Continuous Use Temperature Range	UL 746B	-76 °F - 185 °F -60 °C - 85 °C	-76 °F - 185 °F -60 °C - 85 °C	-76 °F - 185 °F -60 °C - 85 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 212 °F -60 °C - 100 °C
Flammability Rating	UL 94	V-2	V-2	HB	V-2	V-2	V-2	HB	V-0
Low Smoke	ASTM E662	PASS	PASS	PASS	PASS	PASS	PASS	PASS	—
Oxygen Index	BS ISO 4589	28	28	—	28	28	28	22	34
Halogen Free	IEC 60754-2	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
Burning Fume Toxicity	BSS-7239	PASS	PASS	PASS	PASS	PASS	PASS	PASS	PASS
Heat Deflection Temperature at 1.9 Mpa	ASTM D648 ISO 75-1/-2	158 °F 70 °C	158 °F 70 °C	145 °F 63 °C	158 °F 70 °C	158 °F 70 °C	158 °F 70 °C	158 °F 70 °C	154 °F 68 °C
Relative Price	—	Low	Low	Low	Low	Low	Med	Med	Med

Recommendation Legend	Highest	High	Acceptable	Low	Lowest
	●	⊖	○	⊖	●

Properties shown are based on data obtained from third party resources and are subject to normal manufacturing tolerances.

Flame Retardant Nylon 6.6	Polypropylene	Weather Resistant Polypropylene	General Purpose ABS	Weather Resistant ABS	TEFZEL	PEEK	Metal Detectable Nylon	Metal Detectable Polypropylene	PVC	Weather Resistant Acetal
Natural	Gray, White, Green	Black	Natural, White, Black, Gray	Black	Aqua Blue	Translucent Brown	Light Blue	Dark Blue	Light Gray	Black
69	14, None, 109	100	None 20, 14	0	76	71	86	186	8	130
11,000	4,100	4,100	6,500	6,500	7,500	15,200	—	—	—	6,500
1.1%	0.1%	0.1%	0.3%	0.3%	<0.03%	0.5%	1.2%	0.1%	0.3%	<0.45%
1 X 10 ⁵	1 X 10 ⁶	1 X 10 ⁶	—	—	1 X 10	1 X 10	—	1 X 10	—	6 X 10
1-2	1-2	7-9	1	7-9	>15	—	—	1	—	>20
⊖	⊖	⊖	⊖	⊖	●	●	○	⊖	○	⊖
⊖	●	●	●	●	●	●	⊖	●	⊖	○
●	○	○	●	●	●	●	●	○	●	●
⊖	○	○	●	●	●	○	⊖	○	⊖	⊖
●	●	●	○	○	●	○	●	●	●	●
⊖	●	●	●	●	●	●	⊖	●	⊖	●
⊖	●	●	●	●	●	⊖	⊖	●	⊖	⊖
-76 °F - 212 °F -60 °C - 100 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 239 °F -60 °C - 115 °C	-76 °F - 158 °F -60 °C - 70 °C	-76 °F - 158 °F -60 °C - 70 °C	-76 °F - 338 °F -60 °C - 170 °C	-76 °F - 464 °F -60 °C - 240 °C (Note 2)	-76 °F - 185 °F -60 °C - 85 °C	-76 °F - 239 °F -60 °C - 115 °C	-40 °F - 122 °F -40 °C - 50 °C	-76 °F - 185 °F -60 °C - 85 °C
V-0	HB	HB	HB	HB	V-0	V-2	HB	HB	HB	HB
—	—	—	—	—	—	PASS	—	—	—	—
34	—	—	18-20	18-20	30	35	—	—	—	—
Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes
PASS	—	—	—	—	—	—	—	—	—	—
154 °F 68 °C	122 °F 50 °C	122 °F 50 °C	210 °F 99 °C	210 °F 99 °C	—	313 °F 156 °C	—	—	—	147 °F 64 °C
Med	Med	Med	Low	Low	High	High	Low	Low	Low	Med

